WESTATLANTIC Tech Corp.
www.westatlantictech.com
sales@westatlantictech.com 902 455 4455

Puddle Flanges seal pipes through concrete walls and floor slaps. Watertight pipe passage.

Puddle Flanges WA-PF models strap around the pipe with 316L stainless steel strap bands
They cast in the wall with the pipe

EDPM PUDDLE FLANGES WITH STAINLESS STEEL Fastener Straps
Pressure Tight up to 145 psi (ft. H2o 334)

Characteristics

EPDM is chemically resistant to a wide range of acids and bases. It also offers outstanding weather and ozone resistance. For applications in connection with oil and petrol, order puddle flanges made in NBR are the preferred option.

Density	1,030 kg /m³
Shore hardness	40° Sh ± 3
Tensile strength	10 N/mm²
Elongation at fracture	750 %
Tear propagation strength	3.9 N/mm²
Temperature resistance	-50....+140 °C
Deformation under pressure (72 h, 70 °C)	32 %

Choosing the right pipe

The EDPM puddle flange can be installed on any type of pipe material, from plastic, steel and stone-ware to concrete, cast iron, fibre cement or GFRP. The EDPM puddle flanges are available for all conventional outside diameters.

Watertight

Wall Sleeves Link Sealing not required.

Puddle Flanges Efficient

EDPM Puddle Flanges Fits American & International Pipe sizes

Cost Effective Pipe sealing

WESTATLANTIC

Puddle flanges, watertight pipe through walls and floors. EDPM Puddle flanges, Frank Puddle flanges, USA and Canada.- USA: Texas, TX, Houston, New York, NY, Illinois, IL, North Dakota, ND, Iowa, IA, Ohio, OH, Michigan, New York, NY, Kentucky, KC, California, CA, Colorado, Denver, Louisiana, LA, Florida, FL., Pennsylvania, PA. Canada, Ontario, Oakville, Toronto, London, Hamilton, Mississauga. Alberta, AB; Edmonton, Fort McMurray Calgary. British Colombia, BC; Kelowna, Vancouver, Prince Rupert, Kitimat. Saskatchewan, SK; Regina, Saskatoon, Prince Albert, Esrevan, Swift Current. Manitoba MB; Winnipeg, Thompson. Quebec, QC; Montreal, Quebec City, Trois-Rieviers, Chebougamau, Sherbrooke Quebec, New Brunswick, NS, Newfoundland.